

### Print carrier

#### JAC® Chromo

is a series of specially coated matt, semi-gloss and gloss papers

**JAC® Chromo Gloss FSC** – the specially coated white, gloss paper face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907, Licence Code: FSC-C004451).

**JAC® Chromo Matt FSC** – the specially coated white, matt paper face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907, Licence Code: FSC-C004451).

**JAC® Chromo Semi Gloss FSC** – the specially coated white, semi-gloss paper face material is made from FSC® certified paper (FSC MIX CREDIT CU-COC-807907, Licence Code: FSC-C004451).

For technical guidance please visit our website under downloads “Guidelines for use – Offset printing

### Average values

	Chromo Gloss FSC	Chromo Matt FSC	Chromo Semigloss FSC
Weight (g/m <sup>2</sup> )	80	90	80
Thickness (µm)	65	77	68
Tensile strength longitudinal (kN/m)	4.8	n.a.	5.2
Opacity (%)	85	91	87
Shelf life of laminate <sup>1)</sup> (years)	2	2	2

<sup>1)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%

For information regarding EHS regulation please visit our web side under downloads “Guidelines for Use “5.12 Product Compliance JAC Offset”

### Adhesive

All 3 adhesives are acrylic dispersion-based, displaying very good application and processing properties including good to excellent guillotining behaviour and very good UV stability.

**D2000** is a general purpose permanent adhesive for most common substrates.

**DURO PLUS** where D2000 is not sufficient like on rough and plastic substrates (as stock article only available with the print carrier 12077).

**NonPerm NP7** is a general purpose removable adhesive. It displays good adhesion on-and residue-free removal from-most smooth, dry surfaces such as glass, metal, polyolefins.

*Note:* For other types of surface, trials under actual application conditions are recommended in order to ascertain suitability.

### Average values

	DURO D2000	DURO PLUS	NonPerm NP7
Adhesion (N/25 mm) (FTM 2 on st. steel/20 min. bond time)	9.2	11	2.6
Tack (N/25 mm) (FTM 9 on glass)	9.6	15.4	3.5
Recommended minimum application temperature (°C)	>+5	>+5	>+5
Heat resistance up to 24 hrs (°C)	+80	+80	+80
up to 1 hr (°C)	+110	+110	+110
Resistance to cold (°C) <sup>2)</sup> down to	- 40	- 40	- 40

<sup>2)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

### Silicone paper

**B 85** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized through a special coating on one side. B85 displays high dimensional stability and excellent flatness.

**B 110** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness.

### Average values

	B 85	B 110
Weight (g/m <sup>2</sup> )	78	86
Thickness (µm)	82	87

#### Guarantee and liability

Issue September 2019

All Avery Dennison and JAC® statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC® products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All Avery Dennison and JAC® products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

