

Metalvac E**TECHNICAL DATA SHEET****Technical specifications**

Property	Test Method	Unit	Tolerance	73	83	93
Substance	ISO 536	g/m ²	± 4 %	73	83	93
Thickness	ISO 534	µm	± 5	63	70	80
Gloss (silver, plain)	ISO 7668	%	± 20 %	500	500	500
Cobb (uncoated side)	ISO 535	g/m ²	± 4	18.0	18.0	18.0
Absolute humidity	ISO 287	%	± 1	5.0	5.0	5.0
Relative humidity	TAPPI T502 om-89	%	± 7	47.0	47.0	47.0
Dry tensile strength MD	ISO 1924 - 2	kg/15mm	-1.0	6.2	7.0	7.5
Dry tensile strength CD	ISO 1924- 2	kg/15mm	-0.5	4.3	5.0	5.5

Values are subject to change without notice.
Last update: 03/16/2020