

Warszawa 04.02.2025

TDS FILE

Folia myMEDIA 1360 Monovinyl WGP

SAP Index MY1360*

Description: Monomeric PVC film, highly stabilized, calendered

Color: White

Surface: Glossy

Glue: waterbase acrylic, permanent transparent

APPLICATION :

For short term outdoor and indoor applications

PRINTING METHOD:

Vinyl is suitable for solvent-based & eco-solvent-based, UV /Latex digital printers

TECHNICAL DATA:

CHARACTERISTIC	TEST METHOD	VALUE
Film thickness	ISO 4593	100 micron monomeric PVC Film
Adhesive type		Clear Acrylic Dispersion, permanent
Liner		One-sided clay-coated Silicone paper (135 g/m ²)
Adhesion:	(Finat FTM 1, after 24 hrs. on Stainless steel)	6,5 N/cm
Dimensional stability:	(Finat FTM 14)	Shrinkage < 0,4 mm
Tensile strength md: Tensile strength cd:	(DIN EN ISO 527) (DIN EN ISO 527)	> 20 MPa > 20 MPa
Elongation md Elongation cd:	(DIN EN ISO 527) (DIN EN ISO 527)	> 160% > 180 %
Application temperature:		> + 10 °C
Temperature durability:		- 40 °C - +80 °C
Outdoor durability:		4 years (unprinted material, vertical outdoor exposure, central European normal climate)

public - 2025-02-04T12:40:09 - a.koscielniak@europapier.pl



HEINZEL
GROUP

EUROPAPIER®

Safety Data Sheet

When used under normal conditions, this product does not generate or release any dangerous substances or hazardous chemicals. This is a non-hazardous product in accordance with the current GefStoffV and EU criteria. Therefore it is not necessary to prepare a Material Safety Data Sheet for this product. The Safety Data Sheet serves only to comply with the regulation to supply information in accordance with REACH Regulation (EC) No. 1907/2006 (REACH) and is available on request. This product is not a hazardous product with regards to transportation legislation; neither does it contain substances that are hazardous to water within the meaning of the federal water act. After use, dispose of the waste product in accordance with the local / national authorities

General Product Information – myMEDIA 1360 Monovinyl WGP

Monomeric PVC-Film (white gloss, - Laminated with a one-sided clay-coated silicone paper (135 g/m²) and equipped with a clear dispersion acrylic adhesive (permanent - Suitable for bonding various surfaces for example on commercial slabs, glass, metal or plastic - Especially suitable for the use on smooth as well as slightly curved surfaces

myMEDIA 1360 Monovinyl WGP is ideal for short term presentation of advertising

Product Advantages

- Very good opacity and flatness characteristics
- Excellent dimensional stability
- Fire classification B1 Certification and in accordance to DIN 4102-1 flame resistant adhered on steel surface
- The film is resistant to the influence of solvent inks during the printing process and excellent printing results are guaranteed with all customary market ECO-Solvent, Solvent, UV and Latex printer

Processing Details and Printing Information

- The print must be completely dry before laminating, a minimum of 48 hours drying time is recommended
- The surface which is to be laminated should be free from any impurities to achieve optimal adhesion to the digital printed film

Transport & Storage

- 2 years if stored in original packaging at ca. 22° C and 50-55% relative humidity
- Printed material should be completely dry and protected during transportation
- Temperature and humidity fluctuations should be avoided

public - 2025-02-04T12:40:09 - a.koscielniak@europapier.pl



HEINZEL
GROUP

EUROPAPIER®

public - 2025-02-04T12:40:09 - a.koscielniak@europapier.pl

**B2B
SHOP**
europapier.pl

Europapier Polska Sp. z o.o., Aleje Jerozolimskie 142 A, 02-305 Warszawa T +48 22 - 356 92 00, F +48 22 - 356 92 90, E-mail: biuro@europapier.pl, www.europapier.pl, Sąd Rejonowy dla m.st. Warszawy w Warszawie, XII Wydział Gospodarczy Krajowego Rejestru Sądowego KRS: 0000112435, Wysokość kapitału zakładowego: 21.020.000,00 zł, REGON: 191095216, NIP: 593-10-92-550, Nr VAT UE PL 5931092550.

Niniejszy dokument ma poufny charakter i jest skierowany wyłącznie do adresata firmy Europapier Polska Sp. z o. o. Bez zgody firmy Europapier Polska Sp. z o. o. nie może być przekazywany do innych odbiorców.