

DirectTex® Softimage Contrast®

Fields of application

.02 .03 .04 .07

Specifications



599150 150



100 % polyester
knit fabrics
PVC-free, recyclable



ca. 160/ 252/ 320/ 505 cm
ca. 63/ 99/ 126/ 199 inch
other widths available on request



B-s1, d0 DIN EN 13501-1
Class A ASTM E84-16



ca. 210 g/m²
ca. 6.2 oz/yd²



ca. 0.37mm
ca. 370 µm



rolls
50/ 100 m
55/ 109 yd



length: 448.7 N
cross: 683.6 N
DIN EN ISO 13934-1



length: 31.4 %
cross: 53.3 %
DIN EN ISO 13934-1



blank: 7
DIN EN ISO 105-B02



blank: 88.76
DIN 5033-1



length: 0.9 %
cross: 0.7 %
DIN EN 14704-1



cold, ultrasonic cut



gain factor
blank: 0,93
DIN 19045-4

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside	•	•	•	•
Outside				

Article shrinkage (33 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	1,2 %	185
190°C	/ %	/ %	
200°C	/ %	/ %	
210°C	/ %	/ %	

Certifications



DirectTex® Softimage Contrast®

Fields of application

.02 .03 .04 .07



Ref.-Nr.: 599150 150 | Preview print sample