

| | | | |
|-------|---------------------|----------|------------|
| Grade | COLOR OFFSET | 0 | 160 |
|-------|---------------------|----------|------------|

| Property | Unit | Average | Range | | NORM |
|---------------------------|---------------------|---------|-------|-------|---------------------------|
| | | | Min | Max | |
| Weight | gr/m ² | 160 | 153,6 | 166,4 | UNE-EN ISO 536 |
| Thickness | μ | 208 | 184,3 | 228,0 | UNE-EN ISO 534 |
| Porosity | ml/min | 1000 | 600 | 1500 | UNE-EN ISO 5636-3 |
| Colour | CMC (1:1) | 0 | 0 | < 1 | ISO 105-J03 |
| Smoothness (inside) | ml/min | 220 | 100 | 700 | UNE-57080-2 ISO 8791-2 |
| Smoothness (outside) | ml/min | 280 | 100 | 800 | UNE-57080-2 ISO 8791-3 |
| Bulk | cm ³ /gr | 1,3 | 1,2 | 1,37 | UNE-EN ISO 534 |
| Moisture | % | 4,5 | 3,5 | 5,5 | UNE-ISO 287 |
| Tensile strenght | m | 5000 | 4000 | 7000 | UNE-EN ISO 1924-2 |
| Tensile strenght | m | 3000 | 2500 | 5000 | UNE-EN ISO 1924-3 |
| Sizing Cobb 60" (inside) | gr.H ₂ O | — | 25 | 35 | UNE-EN ISO 535 |
| Sizing Cobb 60" (outside) | gr.H ₂ O | — | 25 | 35 | UNE-EN ISO 536 |

| |
|--|
| |
|--|