

Grade	COLOR OFFSET	0	240
-------	---------------------	----------	------------

Property	Unit	Average	Range		NORM
			Min	Max	
Weight	gr/m ²	240	230,4	249,6	UNE-EN ISO 536
Thickness	μ	312	276,5	342,0	UNE-EN ISO 534
Porosity	ml/min	1000	600	1500	UNE-EN ISO 5636-3
Colour	CMC (1:1)	0	0	< 1	ISO 105-J03
Smoothness (inside)	ml/min	220	100	700	UNE-57080-2 ISO 8791-2
Smoothness (outside)	ml/min	280	100	800	UNE-57080-2 ISO 8791-3
Bulk	cm ³ /gr	1,3	1,2	1,37	UNE-EN ISO 534
Moisture	%	4,5	3,5	5,5	UNE-ISO 287
Tensile strenght	m	5000	4000	7000	UNE-EN ISO 1924-2
Tensile strenght	m	3000	2500	5000	UNE-EN ISO 1924-3
Sizing Cobb 60" (inside)	gr.H ₂ O	—	25	35	UNE-EN ISO 535
Sizing Cobb 60" (outside)	gr.H ₂ O	—	25	35	UNE-EN ISO 536

--