

Grade	COLOR OFFSET	0	80
-------	---------------------	----------	-----------

Property	Unit	Average	Range		NORM
			Min	Max	
Weight	gr/m2	80	76,8	83,2	UNE-EN ISO 536
Thickness	μ	104	96,0	112,3	UNE-EN ISO 534
Porosity	ml/min	1000	600	1500	UNE-EN ISO 5636-3
Colour	CMC (1:1)	0	0	< 1	ISO 105-J03
Smoothness (inside)	ml/min	180	100	500	UNE-57080-2 ISO 8791-2
Smoothness (outside)	ml/min	190	100	550	UNE-57080-2 ISO 8791-3
Bulk	cm3/gr	1,3	1,25	1,35	UNE-EN ISO 534
Moisture	%	4,7	4	6	UNE-ISO 287
Tensile strenght	m	6000	5000	8000	UNE-EN ISO 1924-2
Tensile strenght	m	3500	3000	5000	UNE-EN ISO 1924-3
Sizing Cobb 60" (inside)	gr.H ₂ O	—	22	35	UNE-EN ISO 535
Sizing Cobb 60" (outside)	gr.H ₂ O	—	22	35	UNE-EN ISO 536

